

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 0 747 525 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: 11.12.1996 Builetin 1996/50

(51) Int. Cl.⁶: **D06N 7/00**

(21) Application number: 96108633.7

(22) Date of filing: 30.05.1996

(84) Designated Contracting States: BE CH DE ES FR GB IT LI NL

(30) Priority: 05.06.1995 US 465235

(71) Applicant: BASF CORPORATION

Mount Olive, New Jersey 08728-1234 (US)

(72) Inventor: Sferrazza, Randall A. Asheville, NC 28804 (US)


(74) Representative: Abel, Manfred et al BASF Aktiengesellschaft Patentabteilung ZDX - C6 67056 Ludwigshafen (DE)

(54) Recyclable carpet and method of recycling

(57) The present invention relates, in general, to recyclable carpet structures. More specifically, the invention relates to a recyclable carpet structure that includes a primary backing having fiber tufts protruding from a top surface thereof, a substrate, and a hot melt

adhesive between the tufted primary backing and the substrate. The invention further relates to a method of recycling such a carpet structure.

FIG.1



EP 0 747 525 A2

10

Description

The present invention relates, in general, to recyclable carpet structures. More specifically, the invention relates to a recyclable carpet structure that includes a primary backing having fiber tufts protruding from a top surface thereof, a substrate, and a hot melt adhesive between the tufted primary backing and the substrate. The invention further relates to a method of recycling such a carpet structure.

Tufted carpet structures are composites in which the pile or tuft-forming fiber is needled through a primary backing. A binding agent is applied to the bottom of the primary backing to hold the tufts in place and to secure the tufted primary backing to a substrate.

Methods have been suggested for recycling various types of carpet structures (including tufted structures) and carpet structures produced from various polymer types (including nylon). In this regard, attention is directed to the disclosures of USP 5,240,530, 5,288,349 20 and 5,370,757 and 5,169,870.

USP 5,240,530 and USP 5,288,349 disclose a carpet that includes a primary backing having tufts of synthetic fibers protruding from a top surface and a secondary backing with an extruded sheet of isotactic polyolefin polymer between and integrally fused to a bottom surface of the primary backing and an upper surface of the secondary backing. The recycling method described includes collecting portions of the carpet, grinding the portions and washing same to separate the various fibers.

USP 5,370,757 teaches a process of manufacturing substantially 100% nylon 6 carpet that includes binding a face yarn of nylon 6 to a support of nylon 6 with molten or dissolved nylon 6. Carpet so constructed is more readily recycled than carpets formed of composites of several different materials.

USP 5,169,870 relates to nylon 6 carpet specifically and to a method of reclaiming ϵ -caprolactam therefrom.

The following patents relate to various other aspects of carpet reclamation: USPs 5,230,473, 5,233,021 and 5,294,384.

The present invention provides a recyclable carpet produced from, for example, two different polymer types. The two types are used, for example, in the primary backing and tufts on the one hand, and the substrate on the other. The backing and substrate are secured together with a hot melt adhesive that has a melt temperature lower than either the backing- or substrate-forming material. The invention also provides a method of recycling such a carpet which takes advantage of the differential melt temperatures of the polymers and the adhesive. The carpet and recycling method of the invention are particularly well suited for use in connection with carpet tile structures

It is an object of the invention to provide a recyclable carpet, including a tufted carpet comprising nylon as one component.

It is a further object of the invention to provide a

method of recycling carpet and, particularly, to a method of reclaiming the hylon component from hylon-containing tufted carpets.

In accordance with the foregoing objectives, the present invention relates to a tufted carpet comprising:

- i) a tufted primary backing comprising tufts of carpet fibers protruding from a top surface of a primary backing,
- ii) a substrate, and
- iii) a hot melt adhesive between a bottom surface of the primary backing and a top surface of the substrate. In the carpet of the invention, the tufts of fibers and the primary backing comprise a first polymer and the substrate comprises a second polymer, which first and second polymers can be the same or different. The hot melt adhesive is selected so as to be compatible with both the first and second polymers and to have a lower melt temperature than the first or second polymers.

The present invention also relates to a method of recycling the above-described carpet. The method comprises: i) heating the carpet to a temperature sufficient to soften the hot melt adhesive but below the melt temperatures of the first and second polymers, and ii) separating the tufted primary backing from the substrate.

Further objects and advantages of the invention will be clear from a reading of the description that follows.

Figure 1 is a cross-sectional view of one emoodiment of the carpet of the present invention. The Figure shows a primary backing having fiber tufts needled therethrough and protruding from a top surface. The Figure also shows a hot meit adhesive between a bottom surface of the primary backing and a top surface of the substrate.

Figure 2 is a side view of an apparatus suitable for use in recycling the carpet illustrated in Figure 1.

The present invention relates to recyclable carpet structures and methods of recycling same. Referring to Figure 1, there is shown a carpet structure of the invention comprising a primary backing (1) that is made of woven fibers. Tufts of carpet face fibers (2) protrude from a top face of primary backing (1) and a thin film of a hot melt adhesive (3) locks the tufts (2) in piace. The hot melt adhesive (3) acts as a buffer between the tufted primary backing (1) and a thermoplastic substrate (4) and secures the tufted primary backing (1) to the thermoplastic substrate (4).

The face fiber tufts and primary backing of the carpet of the invention are formed of the same polymeric material. The substrate is formed of a polymer that can be different from that from which the fiber tufts and primary backing are formed. The hot melt adhesive applied to the back surface of the primary backing to lock the tufts in place and to act as a buffer between the tufted primary backing and the thermoplastic substrate is compatible with the polymers of the tufts, backing and substrate, and has a melt temperature lower than the

10

backing and/or substrate polymers.

Suitable polymers for the fiber tufts and primary backing of the carpet of the invention include nylons (eg nylon 6 and nylon 66), polypropylene and polyesters. Nylon 6 is preferred. The primary backing can take the form, for example, of a woven tape (eg a tape such as those currently used in primary backings), a knit fabric (as described in DE 41 11455 (Nordfaser)), or a nonwoven fabric such as those used in automotive carpet. Films or webs can also be used.

Suitable substrate polymers include thermoplastics, for example, polyolefins, ethylene vinyl acetate (EVA), and polyvinyl chloride (PVC). The substrate can be applied, for example, as a hot-melt or in a solvent carrier (eg for EVA and PVC). The polyolefins can be a fiber but can also be applied as a hot-melt or solvent applied.

The hot melt adhesive applied to the bottom side of the primary backing and the top side of the substrate is selected so as to be compatible with the polymers of the 20 tufted primary backing and the substrate. Advantageously, the adhesive is caprolactam based copolya-Compatible polyolefins and copolyester adhesives can also be used. Examples of suitable adhesives include the Griltex series from Ems and the Vestamelt series from Hüls. The hot melt coating can be applied to the primary backing using various methods of adhesive application, including those described in USP 5,240,530.

The carpet of the present invention can be recycled 30 by heating the carpet to a temperature above the softening point of the hot melt adhesive, but below the melting point of the polymers of the tufted primary backing and substrate. This softening of the hot melt adhecomponents.

One embodiment for separating the carpet into its two components, shown in Figure 2, involves a two stage process on a moving conveyor belt (1). In the first stage, carpet (2) is heated via heater (3). Heating can be effected using infrared heaters, a heated roll, steam injection, microwave radiation and the like. The temperature to which carpet (2) is heated is sufficient to soften the hot melt adhesive but not sufficient to melt the tuft/primary backing and substrate polymers. In the second stage, a splitter (4) (which can be heated) separates the carpet components which can then be separately wound on winders (5) and (6).

An alternative recycling embodiment involves mechanically gripping the fiber tufts prior to carpet heating. Upon heating of the carpet to the hot melt adhesive softening point, the substrate component simply drops off under its own weight and into a recovery area.

Regardless of the technique used for separating the carpet into its two polymer components, the tufted fabric can be recycled, for example, into a recycled resin by cutting and pelletizing or, where economical, by depolymerization in accordance with known techniques. The substrate can, for example, be chopped and recycled back to the substrate or used as a recycled resin.

All documents cited above are hereby incorporated in their entirety by reference.

One skilled in the art will appreciate from a reading of this disclosure that various changes in form and detail can be made without departing from the true scope of the invention.

Claims

- 1. A tufted carpet comprising:
 - i) a tufted primary backing comprising tufts of carpet fibers protruding from a top surface of a primary backing,
 - ii) a substrate, and
 - iii) a hot melt adhesive between a bottom surface of said primary backing and a top surface of said substrate.

wherein said tufts of fibers and said primary backing comprise a first polymer and said substrate comprises a second polymer and wherein said hot melt adhesive is compatible with both said first and second polymers and wherein said hot melt adhesive has a melt temperature lower than melt temperatures of said first and second polymers.

- 2. The carpet according to claim 1 wherein said first polymer is a nyion.
- 3. The carpet according to claim 2 wherein said nylon is nylon 6 or nylon 66.
- sive allows the carpet to be split into the two polymer 35 4. The carpet according to claim 2 wherein said hot melt adhesive is a caprolactam based copolyamide.
 - 5. The carpet according to claim 3 wherein said nylon is nylon 66.
 - 6. The carpet according to claim 5 wherein said hot melt adhesive is a hexamethylenediamine and adipic acid based copolyamide.
 - 45 7. The carpet according to claim 1 wherein said first polymer is polypropylene and said hot melt adhesive is a polyolefin.
 - 8. The carpet according to claim 1 wherein said first polymer is a polyester and said hot melt adhesive is a copolyester.
 - 9. The carpet according to claim 1 wherein said second polymer is a thermoplastic.
 - 10. The carpet according to claim 9 wherein said thermoplastic is polyvinyl chloride.
 - The carpet according to claim 1 wherein said first

and second polymers are different.

12. A method of recycling the carpet according to claim 1 comprising heating said carpet to a temperature sufficient to soften said hot melt adhesive and below melt temperatures of said first and second polymers, and separating said tufted primary backing from said substrate.

10

15

20

25

30

35

40

45

50

55

FIG.1





FIG.2





Europäisches Patentamt

European Patent Office

Office européen des brevets



EP 0 747 525 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3: 01.12.1999 Bulletin 1999/48 (51) Int. Cl.6: D06N 7/00

(11)

(43) Date of publication A2: 11.12.1996 Bulletin 1996/50

(21) Application number: 96108633.7

(22) Date of filing: 30.05.1996

(84) Designated Contracting States: BEICH DE ES FRIGBIT LINL

(30) Priority: 05.06.1995 US 465235

(71) Applicant: BASF CORPORATION Mount Olive, New Jersey 07828-1234 (US) (72) Inventor: Sferrazza, Randall A. Asheville, NC 28804 (US)

(74) Representative: Abel, Manfred et al **BASF Aktiengesellschaft** Patentabteilung ZDX - C6 67056 Ludwigshafen (DE)

Recyclable carpet and method of recycling (54)

The present invention relates, in general, to recyclable carpet structures. More specifically, the invention relates to a recyclable carpet structure that includes a primary backing having fiber tufts protruding from a top surface thereof, a substrate, and a hot melt adhesive between the tufted primary backing and the substrate. The invention further relates to a method of recycling such a carpet structure.

FIG.1





EUROPEAN SEARCH REPORT

Application Number

EP 96 10 8633

Category	Citation of document with inco	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.8)	
X	DE 41 11 455 C (NORD GMBH) 23 July 1992 (* page 3, line 38 -	DEUTSCHE FASERWERKE 1992-07-23) line 54; claims 1,9,10	1-4,9	D06N7/00
X	EP 0 625 605 A (MONS 23 November 1994 (19 * column 4, line 22	ANTO CO) 194-11-23) - line 36; claim 11 *	1-3,5,6,	
X	WO 95 06771 A (FIBER ERIK (DK); JESSEN LA 9 March 1995 (1995-0 * page 16, line 11 - * page 18, line 10 - * page 24, line 24 - * page 25, line 34 -	- line 24 * - page 20, line 32 * - line 33 *	1,2,7-9.	
X	DE 93 14 788 U (LONG BERNDT C) 2 February * page 3, line 1 - p 1,2; figure *	GLIFE TEPPICHBODEN (1995 (1995-02-02) (1995 - 1) (1995 - 2) (1995 - 2)	1.9,11,	TECHNICAL FIELDS SEARCHED (Mt.Cl.6)
X	DE 94 03 111 U (WUD1 23 June 1994 (1994-(* page 3, line 26 ~ 1,2,11; figure * * page 6, line 10 -	06-23) line 32; claims	1-3,5,12	DO6N
X	EP 0 511 469 A (HUEL 4 November 1992 (199 * page 2, line 28 - 1-4,8.11; example * * page 3, line 35 -	line 57; claims	1,2,4,9	
X	NL 8 402 863 A (TAP VISSC) 16 April 198 * page 2, line 28 - figure *	IJTFABRIEK B V V H FA 6 (1986-04-16) page 3, line 35:	1,9,11	
			-	
	The present search report has t			
	Place of search	Date of completion of the search		Examiner
	THE HAGUE	1 October 1999	Pan	nies Olle. S
X pa y pa y pa ob ob ob ob ob ob ob ob ob ob ob ob ob	CATEGORY OF CITED OCCUMENTS inticularly relevant filaken alone inticularly relevant filomolned with anot cument of the same category chnological background pn-written disclosural termediate document.	T theory or princip E earlier patient do after the filling di her D document cited L document cited 5 member of the document	ate in the application for other reasons	kshedion, or s



EUROPEAN SEARCH REPORT

Application Number

EP 96 10 8633

alegory	Citation of document with indica		Relevant	CLASSIFICATION OF THE
vedoi à	of relevant passage:		to claim	APPLICATION (Int.Cl.6)
	EP 0 604 897 A (HOECHS 6 July 1994 (1994-07-0 * column 3, line 30 - * column 5, line 39 -	06) column 5, line 12 *	1,8,9	
	WO 93 13254 A (DU PONT 8 July 1993 (1993-07-0 * page 10, line 12 - * page 12, line 32 -)8) ine 26; example l *	1,7,9	
ι	WO 89 09561 A (ALLIED 19 October 1989 (1989- * claims; examples *	SIGNAL INC) -10-19)	1-6	
1	WO 93 12285 A (PEGULAN 24 June 1993 (1993-06- * claims; examples *		1,2,7-9	
				TECHNICAL FIELDS
				SEARCHED (Int.Cl.6)
	The present search report has been	n drawn up for all claims	1	
	Prace of search	Qate of completion of the search	·	Examiner
	THE HAGUE	1 October 1999	Pam	ies Olle. S
Xipar Yipar doc Alteo	CATEGORY OF CITED DOCUMENTS riticularly relevant if taken alone riticularly relevant if combined with another tument of the same category photological background n-written disclosure	T Theory or principle earlier patent do after the filling date. On cocument cited to document cited to document cited to member of the significant cited.	cument, but public te in the application or other reasons	shed on, or

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 96 10 8633

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

01-10-1999

Patent docume cited in search re		Publication date		Patent family member(s)	Publication date
DE 4111455	C	23-07-1992	AT	142720 T	15-09-19
00 4111433	C	20 0, 13,72	AU	652618 B	01-09-19
			AU	1397292 A	15-10-19
			CA	2065683 A	10-10-19
			CN	1067459 A.B	30-12-19
			CS	9201085 A	14-10-19
			DE	59207082 D	17-10-19
			DK	508287 T	30-09-1
			EP	0508287 A	14-10-1
			ES	2091969 T	16-11-1
					•
			GR	3021067 T	31-12-1
			HR	920068 A	31-08-1
			IL	101440 A	18-06-1
			JP	5214663 A	24-08-1
			MX	9201620 A	01-10-1
			NZ	242194 A	27-04-1
			PL	169756 8	30-08-1
			RO	109565 A	30-03-1
			RU	2085638 C	27-07-1
			TR	26194 A	15-02-1
			US	5494723 A	27-02-1
EP 0625605	Α	23-11-1994	NON	E 	
WO 9506771	A	09-03-1995	AT	154078 T	15-06-1
			AU	680546 B	31-07-1
			AU	7608594 A	22-03-1
			CN	1132533 A	02-10-1
			CZ	9600628 A	12-02-1
			DE	69403674 D	10-07-1
			DE	69403674 T	13-11-1
			DK	724660 T	20-10-1
			EP	0724660 A	07-08-1
			ES	2103604 T	16-09-1
			FI	960956 A	29-04-1
			ĠŔ	3024593 T	31-12-1
			HU	74437 A.B	30-12-1
			JP	2916266 B	05-07-1
			JP	9502491 T	11-03-1
			NO NO	960810 A	30-04-1
			NZ NZ	271960 A	24-11-1
			—		24-11-1
			PL	313266 A	
			SG	47710 A	17-04-1
			\$ K U S	26596 A 5902663 A	08-01-1 11 - 05-1

For more details about this annex see Official Journal of the European Patent Office. No. 12.82

4

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 96 10 8633

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the ourpose of information

01-10-1999

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 9314788	U	02-02-1995	NONE	
DE 9403111	U	23-06-1994	NONE	
EP 0511469	Α	04-11-1992	DE 4114140 A	05-11-199
NL 8402863	Α	16-04-1986	NONE	
EP 0604897	Α	06-07-1994	US 5538776 A	23-07-199
wo 9313254	Α	08-07-1993	US 5256224 A DE 69225810 D DE 69225810 T EP 0619849 A ES 2116434 T JP 7502576 T US 5283097 A	26-10-199 09-07-199 04-02-199 19-10-199 16-07-199 16-03-199 01-02-199
WO 8909561	Α	19-10-1989	US 4871604 A AT 92731 T AU 611552 B AU 3299989 A CA 1323253 A DE 68908408 T EP 0408633 A JP 3503553 T	03-10-198 15-08-199 13-06-199 03-11-198 19-10-199 09-12-199 23-01-199 08-08-199
WO 9312285	Α	24-06-1993	DE 4140580 A DE 4228570 A AU 3086492 A	17-06-199 03-03-199 19-07-199

For more details about this annex see Official Journal of the European Patent Office. No. 12.32